No.


## 1. Scope

This specification covers basic requirements for the structure and optical performances of GHTT-4002.

## 2. Structure

Table 1					GHTT-4002			
Item			Specification					
			Unit	Min.	Тур.	Max.		
Optical Fiber	Core Material		_	Polymethyl-Methacrylate Resin				
	Cladding Material		_	Fluorinated Polymer				
	Core Refractive Index		_	1.49				
	Refractive Index Profile		_	Step Index				
	Numerical Aperture		_	0.5				
	Core Diameter		μm	920	980	1,040		
	Cladding Diameter		μm	940	1,000	1,060		
Jacket	Material		_	Polyethylene				
	Color		_	Black				
	Dimention -	Minor Axis	mm	2.13	2.20	2.27		
		Major Axis	mm	4.2	4.3	4.4		
	Indication on the Jacket		_	Pink line on one of the pair				
Number of cords			_	1 Duplex cord				
Strength Member	Material		_	Aramid Fiber				
Sheath	Material		_	Poly-Vinyl-Chloride				
	Color		_	Gray				
	Diameter		mm	5.8	6.0	6.2		
Approximate Weight			g/m	38				
Indication on the Jacket		_	●●● Å ES	SKA PREMIER	● ● ● : Pink			

## Sectional View



No.

## 3. Performances

Table 2			GHTT-4002				
Item		Acceptance Criterion and/or	Specification				
		[ Test Condition ]	Unit	Min.	Тур.	Max.	
Maximum Rating	Storage Temperature	No Physical Deterioration [ in a Dry Atmosphere ]	$^{\circ}\!\mathbb{C}$	-40	_	+85	
	Operation Temperature	No Deterioration in Optical Properties [in a Dry Atmosphere]	$^{\circ}$ C	-40	ı	+85	
		No Deterioration in Optical Properties** [ under 95%RH condition ]	$^{\circ}$	-	_	+75	
Optical Properties	Transmission Loss	[ 25°C 50%RH ]	dB/km	I	ı	170	
	Collimated Light ]	[ Operation Temperature ]	dB/km	1	I	190	
Mechanical Characteristics A	Minimum Bend Radius	Loss Increment ≦0.5dB [ A Quarter Bend ]***	mm	40	-	-	
	Repeated Bending Endurance	Loss Increment ≦1dB [ in Conformity to the JIS C 6861 ]****	Times	5,000	ı	_	
	Allowable Tension	[ in Conformity to the JIS C 6861 ]	N	420	-	-	
	Twisting Endurance	Loss Increment ≦1dB [ Sample Length : 1m Tensile Force : 4.9N ]	Times	2	_	_	
	Impact Endurance	Loss Increment ≦1dB [ in Conformity to the JIS C 6861 ]	N∙m	0.4	_	_	

All tests are carried out under temperature of 25°C unless otherwise specified.

The specifications is subject to change without notice.

The information contained herein is presented as guide for the product selection.

Please contact our business department for the issue of an official specification sheet.

<sup>\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours.

<sup>\*\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

<sup>\*\*\*</sup> In the direction of the minor axis

<sup>\*\*\*\*</sup> Bend Angle +/-90°, Bend Radius 15mm, Tension 1,000g