



OFS Fitel, LLC

Headquarters

2000 Northeast Expressway

Norcross, GA 30071 USA

Phone:+1 770.798.5555


Phone:+1 888.342.3743 [USA and Canada]

Website: www.ofsoptics.com

Item # CF05578-01, 200 μm HCS 0.43 NA Low OH Optical Fiber

High NA fiber captures more input power with very low bend-induced attenuation, high coupling efficiency.

Part of the HCS fiber family, these fibers are compatible with crimp and cleave termination.



[Optical Properties](#) | [Dimensions/Geometric Properties](#) | [Coating/Buffer Descriptions](#) | [Mechanical and Testing Data](#) | [How To Order:](#) | [Typical Applications](#) | [Options](#)

Optical Properties

Type	Multimode Step-Index
Numerical Aperture	0.43
Attenuation	@ 850 nm, ≤ 6 dB/km
Water Content	Low OH

Dimensions/Geometric Properties

Core Diameter	200 ± 4 µm
HCS® Cladding Diameter	230 +0 / -10 µm
ETFE Buffer Diameter	500 ± 30 µm
Core/Clad Offset	≤ 5 µm
Crimp & Cleave Compatible	Yes

Coating/Buffer Descriptions

Cladding Material	HCS
Buffer Material	ETFE
Operating Temperature	-65 to +125 °C

Mechanical and Testing Data

Short-Term Bend Radius	≥ 10 mm
Long-Term Bend Radius	≥ 16 mm
Proof Test Level	≥ 150 kpsi 1.03 GPa

How To Order:

Product Description Code	HCP-H0200T
Order From Location	AVON LOCATION 1.888.438.9936 toll-free in the United States and Canada 1.860.678.0371 from outside the U.S.A. 55 Darling Drive Avon, CT 06001, USA
Order By Item #	CF05578-01

Typical Applications

High-Power Laser Delivery
Industrial
Medical Illumination
Sensors

Options

Buffer Color
Buffer Diameter
Buffer Material
Cabling
Connectorization
Numerical Aperture
Proof Test